



## Model BB1275H

75AH 12V LiFePO4 Deep Cycle Battery

Data sheet

Electrical Specification		
Voltage	12V	
Capacity	75AH	
Operating Temperature	- 4°F to 135°F	
	(-20°C to 57.2°C)	
Efficiency	99%	
Self Discharge	2-3% per month	
Maximum Series Voltage	48V	
Cycles	3K-5K	
Built-in BMS	Internal	
Resistance	10 mΩ	
Usable DoD	100%	

Discharging Specification		
Max Discharge Current	100A	
Peak Discharge Current	200A for 30 Seconds	
Surge for Loads over 500A	.5 Seconds	
Recommended LVD	10.5V	
BMS Discharge Voltage Cut-Off	10V	
Reconnect Voltage	10V	
Short Circuit Protection	Yes	

Recognized Specification	
Certifications	UL/CSA-62133-2
Shipping Class	UN3480, Class 9

Drawing Specification	
1.09 in -2.21 in -7.5 in	8.93 in
10.49 in	
10.24 in	

Charging Specification		
Recommended Charge Current	.5c	
Max Charge Current	37.5A	
Absorption Voltage	14.2V-14.6V	
Float Voltage	13.4V-13.8V	
Equalization Voltage (if applicable)	14.4V	
	23 Minutes	
Absorption Time	per 75AH	
~	battery bank	
BMS Charge Current Cut-Off	.5C Recommended	
Recharge/Rebulk Voltage	13.3V	
BMS Cell Balancing Voltage Range	14.2V-14.6V	
High BMS Voltage Protection	14.7VDC	
Temperature Compensation	No/Disable	

Mechanical Specification		
Dimensions	10.49"L X 7.11"W X 8.93"H	
Weight	27 lbs.	
Terminal Type	.25" Brass	
Terminal Hole	3/8" hole and 3/8" or 5/16" hardware is suggested	
Terminal Torque	9-11 Ft-lb.	
Case Material	ABS Fire Rated	
Cell Type - Electrolyte	LiFeP04	
Sealed and Water Resistant Case	Non-Submersible	
Heat	Proprietary Internal Heating Solution	
Heat Enable Terminal	Female M4 Terminal	

Temperature Specification		
Discharge Temperature	-4°F to 135°F	
	(-20°C to 57.2°C)	
Charge Temperature	25°F - 135°F	
Storage Temperature	-10°F to 140°F	
	(-23°C to 60°C)	
BMS High Temperature Cut-Off	>135°F	
BMS Reconnect Temperature	<135°F	





## Model BB1275H

75AH 12V LiFePO4 Deep Cycle Battery **Data sheet** 

## **Performed Operation Data** .5C Discharge with Temperature Variations 1C Discharge Voltage with Temperature Variations OF .5C Dischg 32F .5C Dischg 72F .5C Dischg OF 1C Dischg 32F 1C Dischg 72F 1C Dischg -100F .5C Dische -125F .5C Dische .5C State of Charge with Temperature Variations Standard Charge Curve with 3 Stage Charger 24 80 20 16 Volt 12 25 40 ■32F .5C Charge ■ 72F .5C Charge ■ 100F .5C Charge 25°F 24 Hr Period <10°F 20°F 24 Hr Period 15°F 24 Hr Period 5024H Heater Draw Expected in a 24Hr Period 14Ah Consumed 18Ah Consumed Total Cycle Time Ah One Cycle -5 -4 -3 -2 -1 0 1 2 3 4 5 6 7 8 9 10 11 12 13 14 15 16 17 18 19 20 21 22 23 24 25 26 27 28 29 30 3.77 4.21 11.73 8.81

\*Note: The storage temperature range is -10°F to 140°F (-23°C to 60°C). We recommend bringing the Battle Born Batteries to a 100% charge and then disconnecting them completely for storage. After six months in storage, your batteries will remain 75-80% charged.

Storing batteries in subzero weather (- $15^{\circ}$ F or more) has the potential to crack the ABS plastic and more importantly could cause a faster loss of capacity, in some cases drastically more than the typical 2 – 4% per month loss.